

























IN

EN 14411 B I_a GL

										
Non gelive/Frost Proof Ingelift/Frostsicher	Totale/Complete Totale/FAbsolut	Resiste/Resists Resiste/Bestading	40+55 N/mm ²	≤ 0,4 %	PEI V	8	> 0,42	R 10	B	V2
 Per specifiche vedere pagina - For technical specification see page Pour consulter les caractéristiques techniques - Spezifikationen siehe Seite - 9										

OUT

EN 14411 B I_a GL

												
Non gelive/Frost Proof Ingelift/Frostsicher	Totale/Complete Totale/FAbsolut	Resiste/Resists Resiste/Bestading	40+55 N/mm ²	≤ 0,4 %	PEI V	WET > 1 DRY > 1	8	> 0,42	R 12	C	ASTM ≤ 0,60	V2

I valori indicati nella tabella si riferiscono alle prove eseguite sul colore WHITE.

The values in the table refer to the tests performed on color WHITE.

Les valeurs indiquées dans le tableau se réfèrent aux essais exécutés sur le couleur WHITE.

Die in der Tabelle angegebenen Werte beziehen sich auf die Tests die auf dem Farbe WHITE ausgeführt wurden.

Los valores indicados en la tabla se refieren a las pruebas realizadas sobre el color WHITE.

Указанные в таблице значения относятся к испытаниям, проведенным на бежевом оттенке WHITE.